Application No.: NEW Docket No.: 0445-0364PUS1

AMENDMENTS TO THE CLAIMS

1. (Original) An absorbent article having extensibility as a whole and comprising an extensible absorbent member having a number of small absorbent clusters dispersed therein in three dimensions, the small absorbent clusters containing a superabsorbent polymer and fibers.

- 2. (Original) The absorbent article according to claim 1, wherein the absorbent member is stretchable.
- 3. (Currently Amended) The absorbent article according to claim 1-or 2, wherein the absorbent member comprises a web containing crimped fibers, and the small absorbent clusters are dispersed in the web.
- 4. (Currently Amended) The absorbent article according to any one of claims 1 to 3 claim 1, wherein the small clusters are each composed of a superabsorbent polymer particle and a number of fibers adhered to the particle.
- 5. (Original) The absorbent article according to claim 4, wherein the small clusters are obtained by mixing particles of the superabsorbent polymer and the fibers with water, drying the mixture, and grinding the dried mixture to size.
- 6. (Currently Amended) The absorbent article according to any one of claims 1 to 3 claim 1, wherein the small clusters are each composed of a helically crimped fiber, a superabsorbent

3 JWB/clb

Application No.: NEW Docket No.: 0445-0364PUS1

polymer particle, and other fiber, the polymer particle and the other fiber being taken into the helix of the helically crimped fiber.

- 7. (Currently Amended) The absorbent article according to any one of claims 1 to 6 claim 1, wherein the small clusters have an average size of 0.2 to 5 mm.
- 8. (Currently Amended) The absorbent article according to any one of claims 1 to 7 claim 1, wherein the extensibility of the absorbent article is such that, when the absorbent article is 150% extended in its longitudinal direction, maintained in the extended state for 2 hours at 40°C and 80% RH, and released from the extended state, the lengths of the absorbent article measured after 20 seconds and after 5 minutes from the release are from 130% to 150% and from 100% to 130%, respectively, of the initial length.
- 9. (Original) An absorbent article having extensibility and designed not to be less absorbent when 150% extended in its longitudinal direction than before being extended.
- 10. (Original) A stretchable absorbent member comprising a web containing crimped fiber, the web having a number of small absorbent clusters dispersed in the web in three dimensions, the absorbent cluster containing a superabsorbent polymer particle and fibers.

4 JWB/clb